



A **SHERWIN-WILLIAMS** Company



REF : COPR 2016 06

Resucoat™ Profile

DESCRIPTION

Resucoat™ Profile is a 3-pack solvent-free high-build epoxy resin system for application as a non-slip floor coating for light to medium industrial use at a thickness of 200 microns. The coating will provide a textured Gloss coloured finish incorporating an anti-slip aggregate which is dispersed within the material. Applied by roller and paint brush the product is low odour producing a seamless , hard wearing , hygienic floor finish.

ADVANTAGES

- High-build finish
- Solvent free
- Hygienic and easily cleaned
- Good colour stability
- Excellent slip resistance
- Excellent high gloss finish
- Available in a wide range of colours

RECOMMENDED USES

- Food processing and beverage areas
- Chemical plant rooms
- Engineering workshops
- Automotive & aviation areas
- Factory units
- Warehouses
- Excellent for all demarcation and walkways

PRODUCT INFORMATION

System thickness (dry)	Solids content by weight	Pack sizes	Pack make up	Shelf life	Storage
200 microns (Per coat)	100 %	5 kg.	1 x Base - Resucoat HB 1 x Hardener- Resucoat HB 1 x Resucoat Profile Aggregate Pot	12 Months (Base & Hardener)	Keep out of direct sunlight. Store in a dry place, not below 15°C

DRYING TIMES & COVERAGE RATES at 20°C

Coverage rate	Pot life	Recoat time	Light traffic	Full traffic	Full chemical cure
5 kg. will cover 20 sq m @ 200 microns thickness	25 Minutes from mixing	6 hours or once surface has lost tackiness	12 -16 Hours	24 -36 Hours	Up to 7 Days



Specification

Product : Resucoat™ Profile

Finish : Textured Gloss Finish

Thickness : 200 microns

Colour : See RSL Coatings Colour Chart

Products required for this system

Prime : Resuseal WB or Resuprime

System : Resucoat™ Profile at required thickness

Surface Seal : Not required

Preparation

New Concrete Floors: New concrete must be clean, sound, dry and fully cured and surface laitance removed preferably by enclosed shot blasting or mechanical grinding, a minimum strength of 25N/mm² is required.

Existing Concrete Floors: Remove all dirt, oil, grease or other surface contaminants by enclosed shot blasting, scarification or mechanical grinding. Fats, oils or greases must be removed by mechanical means and detergent washing. Local repairs should be carried out using **Resupatch** or **Resuscreed 43**.

Resucoat™ Profile can also be applied to existing coatings and to other cementitious screeds which should be clean and sound with an appropriate mechanical key for adhesion.

Priming

Open, porous substrates may require priming with **Resuseal WB**.

If the substrate appears very weak and dusts easily the matrix of the screed can be strengthened by installing **Resutop Binder** a low viscosity binder formulated for defective substrates. (Contact RSL for further information).

If substrates do have moisture levels above 75% RH prime the surface with **R.S.Dampshield** (number of coats dependent on moisture content).

Application

The ambient temperatures of the areas should not be allowed to fall below 10°C throughout the application and the curing period, as this could have an adverse effect on the appearance and colour of the system. Surface temperature must be above 5°C.

Where possible it is recommended that the application area is heated to a minimum temperature of 15°C ideally to allow the ambient and substrate temperature to stabilise prior to installation.

Mixing: Pre-mix the coloured base component of a **Resucoat™ HB** unit to a uniform consistency then mix the entire contents of the base with the hardener using a slow speed electric mixer for approximately two minutes or until the two components have fully combined. Add the **Resucoat™ Profile** aggregate pot to the mixed **Resucoat™ HB** and mix the full unit for 15 - 20 seconds to ensure the aggregate is evenly dispersed into the **Resucoat™ HB**.

If a separate mixing bucket is being used then mix thoroughly as above ensuring all contents of the 3 components are removed from the buckets supplied.

The mixed unit should be applied immediately by roller or brush with a consistent procedure at an even rate of application. Floor areas should be cross-rolled to ensure even application and to minimise roller marks.

Coverage rates will depend on profile and porosity of the substrate.

Two coats of **Resucoat™ Profile** can be installed or a first coat of **Resucoat™ HB** for a smooth finish followed by a top coat of **Resucoat™ Profile** for a textured finish.

Category Guide

FeRFA Category : 2

Technical Information

The following figures are obtained from laboratory tests and our experience with this product.

Slip Resistance	Dry > 60
Method BS7976 pt1-3 2002	Wet Please consult RSL

The slip resistance of a floor surface can vary as a result of installation process, conditions applying at the time of application and subsequent traffic. Inappropriate cleaning or maintenance can adversely affect the performance. For potential wet areas please consult RSL for further details.

Abrasion Resistance	n/a
Method BS8204 /ASTM D4060	

Temperature Resistance	Tolerant of sustained temperatures of up to 45°C
------------------------	--

Chemical Resistance	Good Chemical Resistance Consult RSL on specific materials
---------------------	---

Compressive Strength	n/a
----------------------	-----

Flexural Strength	n/a
-------------------	-----

Tensile Strength	n/a
------------------	-----

VOC	197 g/l Calculation based on a full mixed unit
-----	---

Life Expectancy	3-4 years plus Subjected to Industrial Traffic RSL terms and conditions will apply
-----------------	--

Maintenance and Cleaning

RSL recommend that **Resucoat™ Profile** should be cleaned with a regular industrial cleaning regime with a floor scrubber utilising **R.S. Industrial Floor Cleaner** or similar with dirty water being removed. Isolated localised cleaning can be carried out using **R.S. Tyre Mark Remover**, **R.S. Fats & Grease Remover** & **R.S. Oil Remover**.

All surfaces should be thoroughly rinsed with clean water after the use of chemical cleaners.

Please refer to the RSL Guide to Cleaning of Resin Floors

Health and Safety

Resucoat™ Profile is formulated from materials designed to achieve the highest level of performance as safely as possible. However, specific components require proper handling and suitable equipment, this information is given in the relevant safety data sheets. In all cases, spillages or skin contamination should be cleaned as soon as practically possible, by dry wiping of the affected area, and thorough washing with soap and water.

The information given in this data sheet is derived from tests and experience with the products and is believed to be reliable. The information is offered without guarantee to enable purchasers to determine for themselves the suitability of the product for their particular application. Any specification or advice given by the Resin Surfaces Limited or its agents is based on the information supplied by the purchaser. Resin Surfaces Limited cannot be held accountable for errors or omissions as a result of that information being incorrect or incomplete. No undertakings can be given against infringement of patents. Some materials are derived from natural sources. As such some variation may occur. Site conditions may also contribute to variation in finish and colour.