



A **SHERWIN-WILLIAMS** Company



REF : TOCC 2016 06

Resutop Cold Cure

DESCRIPTION

Resutop Cold Cure is a fast curing epoxy resin for application at low temperatures down to 5°C as a chemical resistant heavy duty floor coating at a thickness from 200 to 250 microns. The coating will provide a smooth Gloss finish to which anti-slip aggregate can be added if required. Applied by roller and paint brush the product is low odour producing a seamless, hard wearing, hygienic floor finish. Resutop is available as a clear coating or in the RSL range of colours.

ADVANTAGES

- Fast curing at low temperatures
- Solvent free
- Hygienic and easily cleaned
- Good colour stability
- Excellent slip resistance with the inclusion of selected aggregates
- No shrinkage on curing
- Excellent high gloss finish

RECOMMENDED USES

- For fastrack installations
- Cold stores
- Meat industry areas
- Chemical plant rooms
- Automotive & aviation areas
- Can be used as a flood coat for non-slip systems
- Resutop clear used as a seal for various RSL systems

PRODUCT INFORMATION

System thickness (dry)	Solids content by weight	Pack sizes	Pack make up	Shelf life	Storage
200 microns (Per coat)	100 %	2.5 kg. & 5 kg.	1 X Base 1 X Hardener	12 Months (Base & Hardener)	Keep out of direct sunlight. Store in a dry place, not below 15°C

DRYING TIMES & COVERAGE RATES at 5°C

Coverage rate	Pot life	Recoat time	Light traffic	Full traffic	Full chemical cure
5 kg. will cover 20 m ² @ 200 microns thickness	15 Minutes from mixing	18 hours at 5°C	18 hours at 5°C	48 - 72 Hours	Up to 7 Days



Specification

Product : Resutop Cold Cure

Finish : Clear or Coloured Gloss

Thickness : 200 microns

Colour : See RSL Coatings Colour Chart

Products required for this system

Prime : Resuprime Cold Cure

System : Resutop Cold Cure

Surface Seal : Not required

Preparation

New Concrete Floors: New concrete must be clean, sound, dry and fully cured and surface laitance removed preferably by enclosed shot blasting or mechanical grinding, a minimum strength of 25N/mm² is required.

Existing Concrete Floors: Remove all dirt, oil, grease or other surface contaminants by enclosed shot blasting, scarification or mechanical grinding. Fats, oils or greases must be removed by mechanical means and detergent washing. Local repairs should be carried out using **Resupatch** or **Resuscreed 43**.

Resutop Cold Cure can also be applied to existing coatings and to other cementitious screeds which should be clean and sound with an appropriate mechanical key for adhesion.

Priming

Resutop Cold Cure does not have to be primed and a primer would not normally be practical for installations at temperatures down to 5°C.

Application

The ambient temperatures of the areas should not be allowed to fall below 5°C throughout the application and the curing period, as this could have an adverse effect on the appearance and colour of the system. Surface temperature should be above 5°C and free from condensation.

Mixing: Pre-mix the base component to a uniform consistency then mix the entire contents of the base with the hardener. If a separate mixing bucket is being used mix thoroughly ensuring all contents of both components are removed from the buckets supplied. Mix using a slow speed electric mixer for approximately two minutes or until the two components have fully combined.

The mixed unit should be applied immediately by roller or brush with a consistent procedure. Floor areas should be cross-rolled to ensure even application and to minimise roller marks.

Coverage rates and surface finish will depend on porosity of the substrate, and temperature of substrate and material.

Category Guide

FeRFA Category : 3

Technical Information

The following figures are obtained from laboratory tests and our experience with this product.

Slip Resistance	Dry > 60
Method BS7976 pt1-3 2002	Wet Please consult RSL

The slip resistance of a floor surface can vary as a result of the installation process, conditions at the time of application and subsequent traffic. Inappropriate cleaning or maintenance can adversely affect the performance. For further advice on potential wet areas please consult RSL.

Abrasion Resistance	n/a
Method BS8204 /ASTM D4060	

Temperature Resistance	Tolerant of sustained temperatures of up to 45°C
------------------------	--

Chemical Resistance	Good Chemical Resistance Consult RSL on specific materials
---------------------	---

Compressive Strength	n/a
----------------------	-----

Flexural Strength	n/a
-------------------	-----

Tensile Strength	n/a
------------------	-----

VOC	<10 g/l Calculation based on a full mixed unit
-----	---

Life Expectancy	3-4 years plus Subjected to Industrial Traffic RSL terms and conditions will apply
-----------------	--

Maintenance and Cleaning

RSL recommend that **Resutop Cold Cure** should be cleaned with a regular industrial cleaning regime with a floor scrubber utilising **R.S. Industrial Floor Cleaner** or similar with dirty water being removed. Isolated localised cleaning can be carried out using **R.S. Tyre Mark Remover**, **R.S. Fats & Grease Remover** & **R.S. Oil Remover**.

All surfaces should be thoroughly rinsed with clean water after the use of chemical cleaners.

Please refer to the RSL Guide to Cleaning of Resin Floors

Health and Safety

Resutop Cold Cure is formulated from materials designed to achieve the highest level of performance as safely as possible. However, specific components require proper handling and suitable equipment, this information is given in the relevant safety data sheets. In all cases, spillages or skin contamination should be cleaned as soon as practically possible, by dry wiping of the affected area, and thorough washing with soap and water.

The information given in this data sheet is derived from tests and experience with the products and is believed to be reliable. The information is offered without guarantee to enable purchasers to determine for themselves the suitability of the product for their particular application. Any specification or advice given by Resin Surfaces Limited or its agents is based on the information supplied by the purchaser. Resin Surfaces Limited cannot be held accountable for errors or omissions as a result of that information being incorrect or incomplete. No undertakings can be given against infringement of patents. Some materials are derived from natural sources. As such some variation may occur. Site conditions may also contribute to variation in finish and colour.