

Omnisports EXCEL



KEY POINTS

Description :

Vinyl sports floor covering over fibreglass with PVC foam backing. Protected with Top Clean XP® (dirt-resistant treatment for ease of maintenance)

3 types of installation :

- Loose laid
- Glued Installation
- Installation over a Tarkolay

Surface Texture : Sorrent

Installation instructions and maintenance guide :

On request

Dimensions (EN ISO 24341) :



2 m



20.5 lm or 23 lm

Total thickness (EN ISO 24346) :



8.3 mm (± 0,2mm)

Total weight (EN ISO 23997) :



6.15 kg/m² (± 800g)

Technical data in force as from the date of publication (02/2016).

The values above correspond to laboratory test (no in situ test), and are subject to modifications for the benefit of further improvement.

For more detailed technical information, please contact Tarkett.

Colors of the products shown in the photos or samples are indicative only. There may be differences in color, gloss and embossing structure between the products sold and photos or samples.

| Properties | Standards | Omnisports EXCEL |
|------------|-----------|------------------|
|------------|-----------|------------------|

| Sports properties | | |
|-----------------------|------------|-----------|
| Friction | EN 13036-4 | 80 - 110 |
| Shock absorption | EN 14 808 | P1 |
| Vertical deformation | EN 14 809 | |
| Vertical ball rebound | EN 12235 | compliant |

| Classification | | |
|------------------|------------|--------|
| Reaction to fire | EN 13501-1 | Cfl-S1 |

| Technical Characteristics | | |
|--------------------------------|---------------|----------------------------|
| Wear Layer | EN 429 | 0.80 mm |
| Resistance to wear | EN ISO 5470-1 | ≤ 1g |
| Resistance to indentation | EN 1516 | compliant < 0.50mm |
| Behaviour under a rolling load | EN 1569 | < 0.50mm No degradation |
| Resistance to impact | EN 1517 | No degradation |

| Specific Characteristics | | |
|--------------------------|---|--|
| Surface treatment | Topclean X-treme performance protection | |
| Maintenance | | |

COMPATIBLE SLABS: Concrete, asphalt screed, anhydrite screed. Any deviation of the slab must be corrected prior installation (6 mm under a 3m straight edge). We reserve the right to modify these specifications without, however, affecting their compliance with standards.

Omnisports Excel



Tarkett France – 1 terrasse Bellini – Tour Initiale TSA 94200 - 92919 Paris la Défense CEDEX
 TÉL. +33(0)1 41 20 40 40 – FAX +33(0)1 41 20 47 05 – info@tarkett.com
 www.professionals.tarkett.com