

SCHÖNOX® SL

Cement Based Rapid Drying, Smoothing and Finishing Compound

suitable to provide a smooth finish on various substrates in interior areas. SCHÖNOX SL can be installed as a true featheredge.

Product characteristics

- EMICODE EC 1^{PLUS} R: very low emission
- for interior use only
- featheredge achievable
- exceptional hardness and strength
- fast drying in all thicknesses
- suitable for underfloor heating systems
- layer thickness above featheredge up to 1/4", in small, well-defined areas up to 7/8" (on wooden floors up to 1/8")
- suitable for castor wheels loadings according to DIN EN 12529
- very smooth surface
- moisture resistant (interior only), no moisture vapor emission limitations on properly prepared concrete

Applications

SCHÖNOX SL is suitable for patching, smoothing and leveling of:

- concrete, cement substrates
- floor leveling compounds
- gypsum substrates
- old substrates such as ceramic tiles
- old, water-resistant adhesive residues
- wooden substrates

as well as for filling, smoothing and leveling of unheated, cement based substrates under:

- SCHÖNOX Moisture Mitigation Systems

Requirements of substrate

- Subfloors must be smooth, sound, clean, dry and free of any contaminants which may hinder adhesion.
- Surface treatments or any "friable" areas of the subfloor must be mechanically removed back to a sound base and the substrate repaired with SCHÖNOX repair compounds as required.
- This product is not a vapor barrier and will allow free passage of moisture. Follow the directions of the floor covering manufacturer regarding the maximum allowable substrate moisture content and test the substrate prior to installing SCHÖNOX SL. Where substrate moisture exceeds the maximum allowed then application of SCHÖNOX SDG, SCHÖNOX MR 18 or SCHÖNOX EPA may be used to suppress residual moisture.
- Do not use SCHÖNOX SL where hydrostatic pressure conditions exist or where moisture vapor emissions exceed the recommended levels.
- Gypsum substrates should always be dry. Do not use moisture mitigation systems on gypsum substrates.

- Old water-soluble adhesives should be removed completely to the clean substrate, old water-resistant adhesives should be mechanically removed to a thin, well-bonded residue (i.e. using the wet-scraping technique as recommended by the Resilient Floor Covering Institute). The complete mechanical removal of cutback (i.e. grinding, sanding, blasting) can be hazardous as old cutback adhesive may contain asbestos. Do not sand or grind adhesive residue. Harmful dust may result. Inhalation of asbestos dust may cause asbestosis or other serious bodily harm. Please consult the adhesive manufacturer and all applicable government agencies for rules and regulations concerning the removal of flooring and adhesives that contain asbestos. Prime remaining adhesive residues accordingly.

- The use of trowelable patching compounds to mask the presence of adhesive residues can be used successfully, but only when the new adhesive to be used does not react with the old residue, and the floor covering to be installed will not be affected by adhesive bleed-through.

- All cement based or wooden substrates must be solid, thoroughly clean and free of oil, wax, grease, asphalt, latex and gypsum compounds, curing compounds, sealers and any contaminant that might act as a bond breaker. If necessary, mechanically clean the floor down to sound, solid surface.

- Solidly bonded non-porous substrates such as ceramic tile and terrazzo must be thoroughly cleaned and abraded including the complete removal of existing waxes and sealers, dust, dirt, debris and any other contaminant that may act as a bond breaker.

- SCHÖNOX SL can be applied over SCHÖNOX EPA without the need of priming. Apply SCHÖNOX SL after the moisture mitigation system has dried accordingly but within the first 24 hours after the moisture mitigation system was applied.

- The requirements of the relevant valid standards, guidelines and data sheets apply.

- Vacuum substrates thoroughly.

Priming




- porous substrates such as:

- concrete, cement substrates
 - OSB board, plywood (well screwed and/or bonded)
- no priming required.

Technical data

- pot life: approx 10 - 20 minutes
- ready for foot traffic: after approx. 20 minutes
- ready for covering:
 - after approx. 20 minutes when applied as a true featheredge
- working temperature: not below 41°F floor temperature
- coverage (depending on texture of substrate):
 - approx. 200 sq.ft. per unit when applied as a true featheredge
 - approx. 35 sq.ft. per unit at 1/8"
- compressive strength (ASTM C109): 25 N/mm² / 3700 psi at 28 days
- flexural strength (ASTM C348): approx. 7 N/mm² / 1300 psi at 28 days
- UL-classified in accordance with ASTM E84 (ANSI/UL 723): Flame Spread 0; Smoke Development 0

All values are approximate, are subject to local climatic fluctuations based upon conditions at 70°F with atmosphere of less than 65 % relative humidity following the recommended mixing ratio. Do not install underlayment or topping before the substrate has dried thoroughly.



■ non porous substrates such as:

- ceramic tiles (thoroughly cleaned and abraded)
 - terrazzo
 - water-resistant adhesive residues (removed as far as possible)
- no priming required.

■ gypsum substrates (sanded and vacuumed)

prime with SCHÖNOX KH FIX.

Mixing ratio

- mix each 4.5kg / 10lb. bag with 1.9 liters / 2.0 quarts of water

Recommended method of working

- Using a clean mixing bucket, add SCHÖNOX SL to cold, clean water to form a homogeneous mixture. Mix thoroughly for approx. 3 minutes using a heavy-duty drill (min. 600 rpm) is recommended to obtain a lump-free mix. Or mix smaller volumes by hand approx. 2 - 3 minutes to consistency. Apply, smooth and shape the leveling compound using a stainless steel smoother or a smoothing trowel.
- Do not mix more material than can be applied within 15 minutes.
- Protect curing SCHÖNOX SL layers from high ambient temperatures, direct sunlight and draughts.
- Clean tools in water immediately.

Packaging

- 4.5kg / 10lb. net weight in paper bags

Storage

- Store in cool and dry conditions.
 - Shelf life: 12 months unopened.
- End of shelf life as indicated may affect selected product properties such as pot life and setting times, but does not generally indicate the end of the products suitability for the recommended application. Always test in a small, well defined area. In case of doubt contact the SCHÖNOX Technical Department.

Disposal

- Empty packaging and dispose of in accordance with federal, state and local waste disposal regulations.

VOC Content

- 0g/l (calculated), SCAQMD 1113

LEED

May help contribute to LEED certification of projects in the categories:

- EQc2
Low-Emitting Materials – 1 to 3 points
- MR Credit 1.1
Building Reuse-Maintain – Existing Walls, Floors and Roof up to 3 points

■ MR Credit 1.2

Building Reuse-Maintain – Existing Interior Nonstructural Elements 1 point

Environmental Product Declaration (EPD)

- Declaration number: EPD-DIV-2013311-EN

Instructions

- Do not use in areas of constant water exposure (such as swimming pools) as this may jeopardize the performance of the underlayment and the floor covering.
- Always install an adequate number of properly located test areas, to include the finish flooring, to determine the suitability of the product for its intended use. As floor coverings vary, always contact and rely upon the floor covering manufacturer for specific directions such as maximum allowable moisture content, adhesive selection, and intended end use of the product.
- Low substrate temperatures and/or high ambient humidity require longer drying times for primers.

Precautions

- SCHÖNOX SL contains Portland cement. Avoid eye and skin contact. In case of contact, rinse immediately with plenty of water. In case of contact with eyes seek additional medical advice. Mix in a well ventilated area and avoid breathing powder or dust. KEEP OUT OF REACH OF CHILDREN. Carefully read and follow all cautions and warnings on product label. For complete safety information, please refer to the Material Safety Data Sheet, or visit our website at www.schonox.us.
- Never mix with cement or additives other than SCHÖNOX approved products. Observe the basic rules of concrete work. Do not install below 41°F surface temperature. Install quickly if substrate is warm.
- Low in chromate in accordance to REACH.

Limitation of Liability

To the best of our knowledge, the technical data contained herein are true and accurate at the date of issuance but are subject to change without prior notice. We guarantee our product to conform to the specifications contained herein. We make no other warranty or guarantee of any kind, express or implied, including merchantability and fitness for particular purpose. Liability, if any, is limited to replacement of the product or refund of the purchase price. Labor or cost of labor and other consequential damages are hereby excluded. SCHÖNOX does not authorize anyone, including SCHÖNOX Representatives, to make any statements which supersede, modify or supplement the information provided on its printed literature or package labels without written confirmation.

The applicable recommendations, guidelines, regulations and safety data sheets are to be observed, together with the recognized architectural and engineering regulations. We guarantee that our products leave the factory in perfect condition. While our recommendations for use are based on tests and practical experience, they can only provide general guidance without any assurance as to product characteristics, since we have no influence over the conditions on site, the execution of the work or the method of processing. This product data sheet supersedes all previous editions.



The SIKA management system is certified to ISO 9001 and 14001 by SQS.

Sika Deutschland GmbH

Subsidiary Rosendahl
P.O. Box 11 40
D-48720 Rosendahl/Germany
Phone +49 (0) 2547-910-0
Fax +49 (0) 2547-910-101
E-Mail info@schonox.de
<http://www.schonox.us>

In North America provided by:

HPS North America, Inc
Phone: 256.246.0345
Fax: 256.246.0346
Email: info@hpsubfloors.com
<http://www.hpsubfloors.com>

