



Liquasil Ltd
Unit 8 Radway Road
Solihull
West Midlands
B90 4NR
Tel: 0121 709 5352
Web: www.asbestoseal.com

Airless Spray Instructions

We recommend a minimum 3000lb fluid pressure airless spray machine with a twist-type spray gun, using a tip size of 17-21 thou tip size. (0.17 to 0.21mm)

Due to the nature of Liquasil products, removing the filter on airless spray equipment will often produce better results.

Hired equipment is likely to have previously been used for spraying other materials such as emulsions.

Before use, it is therefore important to thoroughly flush the system with Xylene in order to reduce the chance of blockages at the tip.

After use, lines must be thoroughly flushed with virgin Xylene and Liquasil coatings must not be left in the system for any length of time following use, as they could fully cure in the spray lines.

DO NOT USE GUN WASH as these products can contain water which is not compatible with silicone polymers.

IMPORTANT

Always refer to the equipment manufacturer's instruction manual before use as each will have their own safety and pressure recommendations.