

Tapiflex Excellence 65

Specification

Printed vinyl floorcovering on glass fibre non woven PVC back bonding Polyurethane reinforcement.
Product standard: ISO 12618 / EN 651.

Accent Excellence 80

Specification

Compact flexible vinyl floorcovering glass fibre reinforced, printed Polyurethane reinforcement.
Product standard: ISO 10682 / EN 648.

DESCRIPTION & CLASSIFICATION	VALUES	Tapiflex Excellence 65 (Sheet)	Tapiflex Tiles 65	Accent Excellence 80 (Sheet)	Accent Dink (Sheet)	Accent Lay (Tile)
Type of floorcovering	ISO 12618 / EN 651	Heterogeneous Acoustic Vinyl	Heterogeneous Acoustic Vinyl	-	-	-
Wear Layer Binder Content	ISO 10942	Type 1	Type 1	Type 1	Type 1	Type 1
UL Certification	ISO 14042	Yes	Yes	Yes	Yes	Yes
Classification	ISO 10671 - EN 648	36	36	36-43	37	37
TECHNICAL CHARACTERISTICS	VALUES	Tapiflex Excellence 65 (Sheet)	Tapiflex Tiles 65	Accent Excellence 80 (Sheet)	Accent Dink (Sheet)	Accent Lay (Tile)
Surface Treatment		TopClear 3P [®]	TopClear 3P [®]	TopClear 3P [®]	TopClear 3P [®]	TopClear 3P [®]
Total thickness	ISO 24146 - EN 426	2.35 mm	2.55 mm	2.30 mm	2.20 mm	2.20 mm
Wear layer thickness	ISO 24149 - EN 429	0.85 mm	0.85 mm	0.80 mm	0.80 mm	0.80 mm
Total weight	ISO 23881 - EN 430	2.642 g/m ²	2.824 g/m ²	2.780 g/m ²	2.700 g/m ²	2.700 g/m ²
Form of delivery	ISO 24144 - EN 428 Sheet (roll)	Approx. 23 running metres x 200 cm	-	Approx. 23 running metres x 200 cm	Approx. 23 running metres x 100 cm	Approx. 23 running metres x 100 cm
ISO 24142 - EN 427 Tiles (box)	-	-	50 x 50 cm - 20 Tiles/box + 6.00 m ²	-	-	-
TECHNICAL PERFORMANCE	VALUES	Tapiflex Excellence 65 (Sheet)	Tapiflex Tiles 65	Accent Excellence 80 (Sheet)	Accent Dink (Sheet)	Accent Lay (Tile)
Dimensional stability	EN 424	+/- 0.20%	+/- 0.20%	+/- 0.20%	+/- 0.20%	+/- 0.20%
Resistance to fire	EN 13501-1	fl, s1 or s2 on floorcovering substrate A2-s1-d0 or on weakly substrate s1-fl-s2	fl, s1 or s2 on floorcovering substrate A2-s1-d0 or on weakly substrate s1-fl-s2	fl, s1 or s2 on floorcovering substrate A2-s1-d0 or on weakly substrate s1-fl-s2	fl, s1 or s2 on floorcovering substrate A2-s1-d0 or on weakly substrate s1-fl-s2	fl, s1 or s2 on floorcovering substrate A2-s1-d0 or on weakly substrate s1-fl-s2
Anti-scratch test	ISO 24199 - EN 424	0.8 mm	0.2 mm	0.8 mm	0.8 mm	0.8 mm
Residual indentation	ISO 24143-1 - EN 423	Required value: 0.20 mm Average measured value*: 0.20 mm Max. measured value*: 0.20 mm	Required value: 0.20 mm Average measured value*: 0.22 mm Max. measured value*: 0.20 mm	Required value: 0.20 mm Average measured value*: 0.20 mm	Required value: 0.20 mm Average measured value*: 0.20 mm	Required value: 0.20 mm Average measured value*: 0.20 mm
Impact sound reduction	EN ISO 1468-8 EN ISO 1713-2	ΔL _{p,w} 19 dB	ΔL _{p,w} 19 dB	ΔL _{p,w} 19 dB	ΔL _{p,w} 19 dB	ΔL _{p,w} 19 dB
Acoustical improvement	ISO 15709-1	ΔC _w + 0.5 dB - Class A	ΔC _w + 0.5 dB - Class A	ΔC _w + 0.5 dB - Class C	ΔC _w + 0.5 dB - Class B	ΔC _w + 0.5 dB - Class B
Carpet wheel test	ISO 4158 - EN 425	No damage	No damage	No damage	No damage	No damage
Furniture leg	EN 426	No damage	No damage	No damage	No damage	No damage
Electrostatic properties	EN 1825 EN 1826	+ 2 kV on concrete 0.5 x 10 ¹¹ Ω	+ 2 kV on concrete 0.5 x 10 ¹¹ Ω	+ 2 kV on concrete 0.5 x 10 ¹¹ Ω	+ 2 kV on concrete 0.5 x 10 ¹¹ Ω	+ 2 kV on concrete 0.5 x 10 ¹¹ Ω
Total VOC emissions	EN 15057	0.20 g/m ² (after 28 days)	0.20 g/m ² (after 28 days)	0.20 g/m ² (after 28 days)	0.20 g/m ² (after 28 days)	0.20 g/m ² (after 28 days)
Thermal resistance	EN 15057	0.26 m ² K/W	0.26 m ² K/W	0.26 m ² K/W	0.26 m ² K/W	0.26 m ² K/W
Underfloor heating	EN 15057	Subtable	Subtable	Subtable	Subtable	Subtable
Light fastness	ISO 105 456-02	0.6	0.6	0.6	0.6	0.6
Chemical resistance	ISO 24197 - EN 423	High resistance	High resistance	High resistance	High resistance	High resistance
Hygiene		Does not contribute to infection spreading	Does not contribute to infection spreading	Does not contribute to infection spreading	Does not contribute to infection spreading	Does not contribute to infection spreading
Slip resistance	EN 12423 EN 13893	R9/R10/Smooth 0.3-0.4	R9 0.3-0.4	R9/R10/Smooth 0.3-0.4	R9/R10/Smooth 0.3-0.4	R9/R10/Smooth 0.3-0.4
Colour		127	127	127	127	127

The above information is subject to modification for the benefit of further information. (ISO/IEC) *No certification - not binding

Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address chosen for these instructions.

CUSTOMS TARIFF - 48.25.00.00.00.00

Do not forget to apply the CE mark to all products and to display it prominently on all packaging and on the floor covering.

