

Tapiflex Excellence 65

Specification

Printed vinyl floorcovering on glass fibre non woven PVC back bonding Polyurethane reinforcement.
Product standard: ISO 10088 / EN 601.

Accent Excellence 80

Specification

Compact flexible vinyl floorcovering glass fibre reinforced, printed Polyurethane reinforcement.
Product standard: ISO 10082 / EN 648.

DESCRIPTION & CLASSIFICATION	CHARACTERISTICS	Tapiflex Excellence 65 (Sheet)	Tapiflex Tiles 65	Accent Excellence 80 (Sheet)	Accent Unik (Sheet)	Accent Lay (Tile)
Type of floorcovering	ISO 10088 / EN 601	Heterogeneous Acoustic Vinyl	Heterogeneous Acoustic Vinyl	-	-	-
Wear Layer Binder Content	ISO 10042	Type 1	Type 1	Type 1	Type 1	Type 1
UV Certification	ISO 10043	Yes	Yes	Yes	Yes	Yes
Classification	ISO 10071 - EN 648	36	36	36-43	37	-
TECHNICAL CHARACTERISTICS	CHARACTERISTICS	Tapiflex Excellence 65 (Sheet)	Tapiflex Tiles 65	Accent Excellence 80 (Sheet)	Accent Unik (Sheet)	Accent Lay (Tile)
Surface Treatment		TopClear 3P [®]	TopClear 3P [®]	TopClear 3P [®]	TopClear 3P [®]	TopClear 3P [®]
Total thickness	ISO 10146 - EN 426	2.35 mm	2.55 mm	2.30 mm	2.20 mm	2.20 mm
Wear layer thickness	ISO 10149 - EN 426	0.85 mm	0.85 mm	0.80 mm	0.80 mm	0.80 mm
Total weight	ISO 10081 - EN 426	2.642 g/m ²	2.842 g/m ²	2.582 g/m ²	2.502 g/m ²	2.502 g/m ²
Form of delivery	ISO 10144 - EN 426 Sheet (roll)	Approx. 23 running metres x 200 cm	-	Approx. 23 running metres x 200 cm	Approx. 23 running metres x 100 cm	-
	ISO 10142 - EN 427 Tiles (box)	-	50 x 50 cm - 20 Tiles/box + 6.00 m ²	-	-	-
TECHNICAL PERFORMANCE	CHARACTERISTICS	Tapiflex Excellence 65 (Sheet)	Tapiflex Tiles 65	Accent Excellence 80 (Sheet)	Accent Unik (Sheet)	Accent Lay (Tile)
Dimensional stability	EN 424	+0.20%	+0.20%	+0.20%	+0.20%	+0.20%
Resistance to fire	EN 13501-1	B ₁ s1, d0 Flammability substrate A2, G1 or an equivalently substrate B class	B ₁ s1, d0 Flammability substrate A2, G1 or an equivalently substrate B class	B ₁ s1, d0 Flammability substrate A2, G1 or an equivalently substrate B class	B ₁ s1, d0 Flammability substrate A2, G1 or an equivalently substrate B class	B ₁ s1, d0 Flammability substrate A2, G1 or an equivalently substrate B class
Anti-scratch test	ISO 10099 - EN 424	0.8 mm	0.2 mm	0.8 mm	0.8 mm	0.8 mm
Residual indentation	ISO 10143-1 - EN 423	Required value: 0.20 mm Average measured value*: 0.20 mm Max. measured value*: 0.20 mm	Required value: 0.20 mm Average measured value*: 0.22 mm Max. measured value*: 0.20 mm	Required value: 0.20 mm Average measured value*: 0.20 mm	Required value: 0.20 mm Average measured value*: 0.20 mm	Required value: 0.20 mm Average measured value*: 0.20 mm
Impact sound reduction	EN ISO 140-8 EN ISO 1013-2	ΔL _{p,w} 19 dB	ΔL _{p,w} 19 dB	ΔL _{p,w} 19 dB	ΔL _{p,w} 19 dB	ΔL _{p,w} 19 dB
Acoustical improvement	ISO 1013-1	ΔC _w + 0.5 dB - Class A	ΔC _w + 0.5 dB - Class A	ΔC _w + 0.5 dB - Class C	ΔC _w + 0.5 dB - Class B	ΔC _w + 0.5 dB - Class B
Carpet wheel test	ISO 4918 - EN 425	No damage	No damage	No damage	No damage	No damage
Furniture leg	EN 425	No damage	No damage	No damage	No damage	No damage
Electrostatic properties	EN 1825 EN 1826	+ 2 kV on concrete 0.5 x 10 ¹¹ Ω	+ 2 kV on concrete 0.5 x 10 ¹¹ Ω	+ 2 kV on concrete 0.5 x 10 ¹¹ Ω	+ 2 kV on concrete 0.5 x 10 ¹¹ Ω	+ 2 kV on concrete 0.5 x 10 ¹¹ Ω
Total VOC emissions	EN 15075	0.20 g/m ² (after 28 days)	0.20 g/m ² (after 28 days)	0.20 g/m ² (after 28 days)	0.20 g/m ² (after 28 days)	0.20 g/m ² (after 28 days)
Thermal resistance	EN 15087	0.26 m ² K/W	0.26 m ² K/W	0.26 m ² K/W	0.26 m ² K/W	0.26 m ² K/W
Interface heating	EN 15087	Subtable	Subtable	Subtable	Subtable	Subtable
Light fastness	ISO 100 100-400	0.6	0.6	0.6	0.6	0.6
Chemical resistance	ISO 10097 - EN 423	High resistance	High resistance	High resistance	High resistance	High resistance
Hygiene		Does not contribute to infection spreading	Does not contribute to infection spreading	Does not contribute to infection spreading	Does not contribute to infection spreading	Does not contribute to infection spreading
Slip resistance	EN 12423 EN 13893	R9 0.3	R9 0.3	R9/R10 0.3	R9/R10 0.3	R9/R10 0.3
Colour		127	127	127	127	127

The above information is subject to modification for the benefit of further information. (ISO/IEC) *No certification - not binding

Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address chosen for these instructions.

CUSTOMS TARIFF - 48.25.00.00.00.00

Do not forget to sign up to the Tarkett newsletter to receive the latest news on our products and services. Sign up now to receive the latest news on our products and services.



WESTERN EUROPE: Austria: Tarkett Holding GmbH, Wiedner Hauptstr. 14, A-1040 Vienna Austria; Belgium: Tarkett Parquet S.A., Rue de la Woluwe 62, B-1200 Brussels Belgium; Denmark: Tarkett A/S, Høje Taastrup Denmark; France: Tarkett Parquet S.A., 10 rue de la Woluwe 62, B-1200 Brussels Belgium; Germany: Tarkett Parquet S.A., 10 rue de la Woluwe 62, B-1200 Brussels Belgium; Greece: Tarkett Parquet S.A., 10 rue de la Woluwe 62, B-1200 Brussels Belgium; Ireland: Tarkett Parquet S.A., 10 rue de la Woluwe 62, B-1200 Brussels Belgium; Italy: Tarkett Parquet S.A., 10 rue de la Woluwe 62, B-1200 Brussels Belgium; Netherlands: Tarkett Parquet S.A., 10 rue de la Woluwe 62, B-1200 Brussels Belgium; Norway: Tarkett Parquet S.A., 10 rue de la Woluwe 62, B-1200 Brussels Belgium; Poland: Tarkett Parquet S.A., 10 rue de la Woluwe 62, B-1200 Brussels Belgium; Portugal: Tarkett Parquet S.A., 10 rue de la Woluwe 62, B-1200 Brussels Belgium; Romania: Tarkett Parquet S.A., 10 rue de la Woluwe 62, B-1200 Brussels Belgium; Spain: Tarkett Parquet S.A., 10 rue de la Woluwe 62, B-1200 Brussels Belgium; Sweden: Tarkett Parquet S.A., 10 rue de la Woluwe 62, B-1200 Brussels Belgium; Switzerland: Tarkett Parquet S.A., 10 rue de la Woluwe 62, B-1200 Brussels Belgium; Turkey: Tarkett Parquet S.A., 10 rue de la Woluwe 62, B-1200 Brussels Belgium; United Kingdom: Tarkett Parquet S.A., 10 rue de la Woluwe 62, B-1200 Brussels Belgium; USA: Tarkett Parquet S.A., 10 rue de la Woluwe 62, B-1200 Brussels Belgium.