



Rely on it.

RENOLIT ALKORPLAN⁸¹⁰³⁸

PVC seam sealer



EXCELLENCE
IN ROOFING

RENOLIT ALKORPLAN⁸¹⁰³⁸

PVC seam sealer

Solution of flexible polyvinyl chloride (PVC-P) in tetrahydrofuran (THF)

PRODUCT DATA

Appearance	Volatile, mobile liquid		
Odour	ethereal		
Consistency	Viscous, 1200 mPa.s at 20°C		
Flash point	-17°C		
Boiling point/range	65-66°C		
Flammability (solid/gas)	Upper explosion limit: 12 %(V) Lower explosion limit: 1.5 %(V)		
Colours	copper green (60884)	terracotta (82119)	light grey (71004)
	charcoal (79851)	white (90300)	grey (73321)

APPLICATION

- Reinforcement of welded joints, T borders and corners for RENOLIT ALKORPLAN waterproofing membranes.
- Shake well before use.
- Dilute only with THF.
- Consumption: approximately 10g/lm
- See RENOLIT ALKORPLAN installation instructions.

PACKAGING

Type	Colour	Packaging	Content	Unit
81038010	60884	1L	Can	6
81038011	82119	1L	Can	6
81038004	71004	1L	Can	6
81038006	79851	1L	Can	6
81038030	90300	1L	Can	6
81038024	73321	1L	Can	6

STORAGE

- Store in dry unheated places, in original packaging. Protect from sun and frost.
- Ventilate well during and after application.
- Regulations concerning flammable liquids must be observed.
- Do not empty into drains. Take precautionary measures against static discharges.
- Refer to the text on the label and take into consideration the data given on the material safety data sheet, which is available on request.

TRANSPORT

Proper shipping name: ADHESIVES (CONTAINS TETRAHYDROFURAN)
IMDG/IATA/ADR: Flammable Liquids; Class 3 PKg Gr II; UN Nr 1133

WWW.RENOLIT.COM/ROOFING

RENOLIT Cramlington Ltd
Station Road, Cramlington, Northumberland NE23 8AQ - United Kingdom
T +44 1670 718283 - F +44 1670 590096 - renolit.cramlington@renolit.com

RENOLIT Belgium N.V - Export Dpt. - Industriepark De Bruwaan 43 - 9700 Oudenaarde - Belgium
T B +32 55 33 98 51 - F +32 55 31 86 58 - renolit.belgium@renolit.com



Rely on it.