

RENOLIT ALKORPLAN

35x76 Walkways

PRODUCT INFORMATION

RENOLIT ALKORPLAN_{35X76}

Laminated membrane of flexible PVC with woven polyester reinforcing. Independently conducted tests have classified the embossing pattern as "very safe" in dry conditions, and "very safe to safe" in wet conditions. (BST)*

Application

Walkway membrane for delineating maintenance, access and emergency routes. The RENOLIT ALKORPLAN_{35X76} walkway can be used as a waterproofing membrane in its own right.



| Product Data | Method | Average production values RENOLIT ALKORPLAN _{35X76} 1,2 mm | Units |
|---------------------------------------|----------------|---|---------|
| Tensile strength | EN 12311-2 (A) | 1286 | N/50 mm |
| | | 1270 | N/50 mm |
| Elongation at break | EN 12311-2 (A) | 18 | % |
| | | 21 | % |
| Dimensional stability | EN 1107-2 | -0.15 | % |
| Cold crack temperature (-20°C) | EN 495-5 | -25 | °C |
| Tear strength | EN 12310-1 | 543 | N |
| | | 581 | N |
| Lamination strength | EN 12316-2 | 178 | N/50 mm |
| Water vapour diffusion resistance (μ) | EN 1931 | 20,000 | - |
| Resistance to static perforation | EN 12730 | 20 | Kg |

| Size/Weight | Thickness | Width | Weight | Roll length | Roll weight |
|------------------------------------|-----------|--------|------------------------|-------------|-------------|
| RENOLIT ALKORPLAN _{35X76} | 1.2 mm | 1.05 m | 1.53 kg/m ² | 25 ml | ca. 40 kg |

Standard conditions of sale are included in price lists, all sales of RENOLIT products are made under these conditions. RENOLIT ALKORPLAN is delivered in rolls. Every delivery may contain up to 10% of short rolls (minimum length: 8 m).

Storage: store dry. Rolls to be parallel and in original packing where possible, do not stack in cross form or under pressure.

* Bergische Universität GH Wuppertal

WWW.RENOLIT.COM/ROOFING

RENOLIT Cramlington Ltd
Station Road, Cramlington, Northumberland NE23 8AQ - United Kingdom
T +44 1670 718283 - F +44 1670 590096 - renolit.cramlington@renolit.com



Rely on it.