

1. Application

SPORTEC® splash offers the same outstanding properties and application options as **SPORTEC® color**. It is a rugged, easy-to-clean and water-repellent floor covering material for use in fitness and gym facilities, retail outlets, exhibition halls, equipment storage rooms and ice sports stadiums. Thanks to the incorporation of large and small EPDM colour granules, **SPORTEC® splash** floor coverings are available in an even greater range of colours and finishes. **SPORTEC® splash** makes your rooms not only very attractive, but also safe and comfortable.

2. Material

Fine-grained recycled tyre rubber (black) and coloured EPDM granules bonded with polyurethane elastomer.

3. Product Design

Colours:



black-bright blue, black-bright red, black-bright green,
black-bright yellow, black-bright orange
(other colours on request)

low colour differences are conditional of material

fine granule structure with coloured EPDM granules

Surface:

4. Dimensions/Tolerances

Width:	1,500 mm (± 1.5 %)	
Thickness:	4, 5, 6, 8, 10 and 12 mm (± 0.3 mm)	
Volumetric weight:	approx. 1,050 kg/m ³	
Roll length (± 1.5 %):	30 m (at 4 mm)	15 m (at 8 mm)
	24 m (at 5 mm)	12 m (at 10 mm)
	20 m (at 6 mm)	10 m (at 12 mm)
	Area weight:	approx. 4.2 kg/m ² (4 mm)
	approx. 5.3 kg/m ² (5 mm)	approx. 10.5 kg/m ² (10 mm)
	approx. 6.3 kg/m ² (6 mm)	approx. 12.6 kg/m ² (12 mm)



The product data sheet is not subject to any change service! All information is without guarantee.
Latest version of this document available on www.kraiburg-relastec.com/sportec

5. Product Testing

Fire resistance:	E _{fl} (B2)	(EN 13501-1)
Tensile strength:	min. 1.5 N/mm ²	(EN ISO 1798)
Elongation at break:	min. 80 %	(EN ISO 1798)
Hardness:	60 ± 5 Shore A	(DIN 53505)
Temperature range:	-30°C to 80 °C	(internal tested)
Abrasion:	max. 200 mm ³	(DIN 53516)
Coefficient of friction:	> 0.30μ (DS)	(EN 13893)
Anti-slip property:	R 10	(DIN 51130)
Step sound insulation:	17 dB (at 6 mm) 18 dB (at 8 mm)	(DIN EN ISO 140-8:1998-03) (DIN EN ISO 140-8:1998-03)
Remaining deformation:	0.21 mm (at 6 mm) 0.13 mm (at 8 mm)	(EN 433:1994-11) (EN 433:1994-11)
Compression set:	approx. 15 %	(internal tested)
Wear hardness:	approx. 4.0 MPa (at 5 mm thickness)	(internal tested)
Electrostatic properties:	0.5 kV	(DIN EN 1815:1995-06)
Light fastness:	2-3	(DIN EN 105-B02:1999-09)
Castor chair suitability:	for permanent use adapted (DIN EN 1307: 1997-06) (Tested at 6 mm and 8 mm thickness)	

6. Installation

Installation has to be done in accordance to the Installation Recommendation of **SPORTEC® splash**. The latest version of the Installation Recommendation can be downloaded at the website of KRAIBURG Relastec GmbH & Co. KG.

7. Sealing

It is recommended to seal the floor covering **SPORTEC® splash** with 2 components PU sealer system "RZ turbo protect" which is available directly from our company. Small damages at the sealed surface can be tread afterword by using a „RZ Refresher Set“ to retain the visual effect.

The product data sheet is not subject to any change service! All information is without guarantee. Latest version of this document available on www.kraiburg-relastec.com/sportec

