



FILL AND FIX

Aerosol and Gun Grade Expanding Foam

Description

A fast setting, multi-purpose PU foam which bonds, fills, seals and insulates most construction materials.

Bond It **EXPANDING FOAM** is a one-component polyurethane assembly foam, and is based on a moisture curing polyurethane prepolymer.

Uses

The fresh foam adheres to all common building materials except from surfaces such as polyethylene, silicone, oil and grease and similar substrates.

Areas of Application:

- ◆ window setting (where a clean and controlled backfill is required),
- ◆ roller shutters (sealing of connection joints),
- ◆ entrance door linings,
- ◆ any kind of small breakthroughs in walls and other cavities.
- ◆ pipe and cable entries.

Properties

The foam can be used at temperatures from +5°C to +25°C. The cured foam is semi-rigid and predominantly close-celled. It is resistant to temperatures ranging from -40°C to +100°C and to ageing, but not to UV-rays. Noise and heat insulation values are excellent.

Preparation

Surfaces to be bonded must be firm, clean, dry and free from dust, grease or contaminants that may hinder adhesion. They must be moistened well with water. All construction components must be properly prepared prior to foam application. It is advisable to have Foam Cleaner at hand.

The ideal working temperature for both the can and environment is +20°C. Chilled cans must be carefully warmed in luke-warm water before usage. However, the can must not be heated above +50°C, as there is a risk of bursting. Cans which are too hot, for example after having been left in a vehicle during summer, must be cooled in water. The can should be shaken occasionally during this process to obtain the required temperature faster.

Prior to work, and before the adaptor is attached, the can must be shaken thoroughly at least 15 - 20 times. Then the adaptor is attached firmly to the valve. Care must be taken not to overtighten the adaptor and not to activate the valve during this process.

Application

The instructions for the can must strictly be observed. The fresh foam will expand by 1½ to 2 times. Therefore care must be taken not to overfill joints. Fresh foam spills

must be removed immediately within the tack-free time with Foam Cleaner. Cured foam must be removed mechanically.

Please Note: Moisture is needed for an even and rapid curing of the foam. Inadequate moistening or overfilling of joints and cavities may lead to an unwanted post-expansion of the foam.

Foam extrusion can be controlled accurately by varying the pressure or by tilting the adaptor. For foam extrusion the valve is pointed down. The valve lever is to be activated carefully.

Once a can has been started, it should be used within four weeks.

Container Size

500ml & 750ml aerosol can.

Storage Conditions

Store and transport upright, in cool, dry conditions (Considerably higher temperatures may reduce the shelf-life). Shelf life is 12 months dependant on storage conditions.

Disposal of Containers

Do not leave empty containers where residue could be harmful to children, animals or the environment. Replace lids and remove any containers to a central disposal point in accordance with local regulations. Do not pierce can. In the event of spillage remove all sources of ignition, ventilate the area, remove people from confined areas. Material should be mopped up immediately with an inert absorbent material such as sand.

Health & Safety

Extremely flammable aerosol. Pressurised container: May burst if heated. Harmful if swallowed or if inhaled. Causes skin irritation. May cause an allergic skin reaction. Causes serious eye irritation. May cause allergy or asthma symptoms or breathing difficulties if inhaled. May cause respiratory irritation. Suspected of causing cancer. May cause harm to breast-fed children. May cause damage to organs through prolonged or repeated exposure. Very toxic to aquatic life with long lasting effects. If medical advice is needed, have product container or label at hand. Keep out of reach of children. Read label before use. IF ON SKIN: Wash with plenty of soap and water. IF INHALED: Remove victim to fresh air and keep at rest in a position comfortable for breathing. IF IN EYES: Rinse cautiously with water for several

minutes. Remove contact lenses, if present and easy to do. Continue rinsing. Dispose of the contents/containers in accordance with the current legislation on waste treatment. Pressurised container: protect from sunlight and do not expose to temperatures exceeding 50°C. Do not pierce or burn, even after use. Do not spray on a naked flame or any incandescent material. Keep away from sources of ignition - No smoking. Contains isocyanates. Persons already sensitised to diisocyanates may develop allergic reactions when using this product. Persons suffering from asthma, eczema or skin problems should avoid contact, including dermal contact, with this product. This product should not be used under conditions of poor ventilation unless a protective mask with an appropriate gas filter (i.e. type A1 according to standard EN 14387) is used.

Specification Summary

(determined at +20°C, 50% relative air humidity)

Yield, free expansion	bulk density approx 20-25 kg/m ³
500 ml can	approx 25 litres
750 ml can	approx 38 litres
Raw density (confined space)	approx 25 kg/m ³
Cell-structure	medium-fine
Tack-free	12-16 minutes
Cutable (20 mm bead)	after 30-40 minutes
Full stability load bearing (20 mm bead)	after approx 18 hours
Minimum working temperature (Can, application surfaces)	+5 °C
Maximum working temperature (Can, application surfaces)	+25 °C
Optimum working temperature (Can, application surfaces)	+20 °C
Tensile strength (in accordance to DIN 53430)	18 N/cm ²
Elongation at tension (in accordance to DIN 53430)	30 %
Compressive strength at 10% stress (in accordance to DIN 53421)	1.5 N/cm ²
Thermal conductivity approx.	0.034 W/mK
Temperature resistance of the cured bead	
Long-term	-50 °C to +90 °C
Short-term	-650 °C to +130 °C

Container Sizes:

Code:	BDFIX500	BDFIX750	BDFIXG750
Size:	500ml	750ml	750ml Gun Grade
Barcodes:	5060021361899	5060021361905	5060021361912

The data given herein is intended as a general guideline only. Actual results achieved may vary with working conditions and the materials involved; which are beyond the control of the manufacturer. Results achieved may not constitute any ground for a claim against the manufacturer. The manufacturer can only guarantee the quality of the product itself. This data sheet cancels and replaces all previous editions.



Certificate Number: 6152
ISO 9001
ISO 14001



BOND IT
Unit G16 River Bank Way, Lowfields Business Park,
Elland, West Yorkshire HX5 9DN.
Telephone: +44 (0)1422 315300 Fax +44 (0)1422 315310
Email: sales@bond-it.co.uk Website: www.bond-it.co.uk



V4 16/11/15
Supersedes: V3 02/02/15