





High Modulus Marine Silicone Sealant



A high quality, non-shrinking, marine quality silicone sealant and adhesive.

HA6 surpasses the requirements of BS EN 15651-1,2:2012. It is unaffected by UV, ozone, salt water immersion and extremes of temperature and is non-slumping in paste form.

Uses

Bond It HA6 contains no fungicides or oils which may leach into water and is therefore recommended for bonding, bedding and sealing glass in aquarium construction. HA6 is also recommended for the manufacture of in-situ gaskets and seals for pumps and pipework to prevent water ingression and as a dust and weatherproofing seal for cabinets in dirty environments or external applications.

It is ideal for use on:

- glass
- ceramics
- anodised aluminium
- primed metals and timber
- many plastics

Preparation

Ensure all surfaces are clean, dry and free from grease, oil or any other contaminants that may hinder adhesion. Prime porous surfaces and metals other than anodised aluminium or stainless steel for optimum adhesion.

Application

Apply using a standard sealant gun with the nozzle cut at an angle of 45°, and to an opening slightly larger than the joint to be sealed.

For sealing and bedding apply in the normal fashion and tool to a smooth finish one or two minutes after gunning. As an adhesive bring the two surfaces together before skinning commences and do not stress the joint before the silicone has developed strength. As a gasket apply to one surface and if the joint is to be broken allow a strong skin to develop before compressing for permanent gaskets the joint can be sealed

immediately. Clean away any excess with white spirit.

Limitations

For concrete and cement surfaces Bond It LN7 neutral cure silicone is recommended. Do not use on surfaces where water can penetrate through porous materials to the bond interface without first carrying out remedial work.

Colours

HA6 comes in 5 colours: white, translucent, black, brown and grey.

Container Size

310ml plastic cartridge.

Shelf Life

24 months in unopened cartridge.

Storage Conditions

Store in cool, dry conditions.

Disposal of Containers

Do not leave empty containers where residue could be harmful to children, animals or the environment. Remove any containers to a central disposal point in accordance with local regulations.

Health & Safety

- Avoid eye contact.
- Avoid prolonged contact with skin.
- Thoroughly wash hands with soap and water after use
- Keep out of reach of children.
- See separate material safety data sheet for full handling, use and storage.



Specification Summary Flammability Non Flammable **Tooling Time** 5-10 minutes Tack Free 10-20 minutes Full Cure 3mm depth per day **Application Temperature** +5°C to + 25°C Rubber Shore A: 25 Hardness 300% Maximum Extensibility Joint Movement Capability 25% by ISO methods Service Temperature Limits -60°C to +180°C. Short periods over 200°C



BOND IT

G16 River Bank Way, Lowfields Business Park, Elland, West Yorkshire. HX5 9DN

14

EN15651-1.2

F EXT-INT, G 25LM CC

Facade sealant for exterior and interior use. Suitable for use in cold climates.

Reaction to fire	Е
Release of chemicals	None
Resistance to flow	≤ 3mm
Loss of volume	<u>≤</u> 10%
Tensile properties after water immersion	NF
Durability	Pass

Container Sizes:

Colour:	Black	Grey	Translucent	White	Brown
Code:	BDHA6BL	BDHA6GR	BDHA6T	BDHA6WH	BDHA6BR
Size:	310ml	310ml	310ml	310ml	310ml
Barcode:	5060021360045	5060021360052	5060021360069	5060021360076	5060021363169

are not detrimental to sealant performance

The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies raw materials are also being used. The recommendations do not absolve the user from the obligation of investigating the possibility of infringement of third parties rights and, if necessary clarifying the position. Recommendations for use do not constitute a warranty, either expressed or implied, of the fitness or suitability of the products for a particular purpose.







Telephone: +44 (0)1422 315300 Fax +44 (0)1422 315310 Email: sales@bond-it.co.uk Website: www.bond-it.co.uk

