

# Vylon Plus

- └ Versatile flooring
- └ Harmonious and fresh colours
- └ Tough and durable
- └ Most flexible in its category



21 000 583 21 007 583 21 001 583	21 000 580 21 007 580 21 001 580	21 000 586 21 007 586 21 001 586	21 000 592 21 007 592 21 001 592	21 000 590 21 007 590 21 001 590
--	--	--	--	--



21 000 591 21 007 591 21 001 591	21 000 589 21 007 589 21 001 589	21 000 588 21 007 588 21 001 588	21 000 596 21 007 596 21 001 596	21 000 585 21 007 585 21 001 585
--	--	--	--	--



21 000 587 21 007 587 21 001 587	21 000 582 21 007 582 21 001 582	21 000 581 21 007 581 21 001 581	21 000 595 21 007 595 21 001 595	21 000 594 21 007 594 21 001 594
--	--	--	--	--



21 000 597 21 007 597 21 001 597	21 000 584 21 007 584 21 001 584	21 000 593 21 007 593 21 001 593
--	--	--

Compact

Homogeneous

Contract Plus p. 82-83

Standard Plus p. 84-85

Vylon Plus p. 86-87



## Plus

The universal flooring solution.

Tarkett's Plus range offers durable, multi-purpose homogeneous vinyl floorings that are excellent value for money. With a colour range that mixes classic standards and contemporary trends, Plus is an ideal solution for the education, retail and commercial sectors.

Tarkett Plus also provides non-linear designs that are totally new for homogeneous floorings in this segment.

The Plus range is equipped with PUR surface treatment for protection and easier initial maintenance.

The PUR also provides a good base for future maintenance procedures.

All PLUS floorings contain non-phthalate plasticizers and contribute to an optimal indoor air quality with VOC emissions below quantifiable level.

Technical data		Contract Plus	Standard Plus 2.0 mm	Standard Plus 1.5 mm	Vylon Plus
<b>Classification</b>	ISO 10581 (EN 649)	Classes: 34	Classes: 34	Classes: 32	Classes: 34
	commercial	43	43	41	43
	industrial				U4 P3 E2/3 C2
	UPEC Classification				312-024.1
	NF UPEC certificate number (Ref NF189)				
<b>Total thickness</b>	ISO 24346 (EN 428)	2.00 mm	2.00 mm	1.5 mm	2.00 mm
<b>Total weight</b>	ISO 23997 (EN 430)	3150 g/m <sup>2</sup>	3 300 g/m <sup>2</sup>	2 475 g/m <sup>2</sup>	3 700 g/m <sup>2</sup>
<b>Surface treatment</b>	—	PUR	PUR	PUR	Factory finish
<b>Abrasion group</b>	EN 660-2	Group P: ≤ 4.00 mm <sup>3</sup>	Group P: ≤ 4.00 mm <sup>3</sup>	Group P: ≤ 4.00 mm <sup>3</sup>	Group M: ≤ 7.50 mm <sup>3</sup>
<b>Volume loss</b>					
<b>Residual indentation</b>	ISO 24343-1 (EN 433)	Approx. 0.04 mm	Approx. 0.04 mm	Approx. 0.04 mm	Approx. 0.04 mm
<b>Castor wheel test</b>	ISO 4918 (EN 425)	Suitable	Suitable	Suitable	Suitable
<b>Dimensional stability</b>	ISO 23999 (EN 434)	Rolls: ≤ 0.40 %	Rolls: ≤ 0.40 %	Rolls: ≤ 0.40 %	Rolls: ≤ 0.40 %
		Tiles: ≤ 0.25%	Tiles: ≤ 0.25%	Tiles: ≤ 0.25%	Tiles: ≤ 0.25%
<b>Reaction to fire</b>	EN ISO 13501-1	B <sub>f</sub> s1	B <sub>f</sub> s1	B <sub>f</sub> s1	B <sub>f</sub> s1
	EN ISO 9339-1	≥ 8 kW/m <sup>2</sup>	≥ 8 kW/m <sup>2</sup>	≥ 8 kW/m <sup>2</sup>	≥ 8 kW/m <sup>2</sup>
	EN ISO 11925-2	Pass	Pass	Pass	Pass
<b>Marine equipment</b>	IMO FTPC Part 5 and 2 IMO Res. A653				
<b>Static electrical charge</b>	EN 1815	< 2 kV	< 2 kV	< 2 kV	< 2 kV
<b>Light fastness</b>	EN ISO 105-B02	≥ 6	≥ 6	≥ 6	≥ 6
<b>Chemical resistance</b>	ISO 26987 (EN 423)	Good resistance	Good resistance	Good resistance	—
<b>Slip resistance</b>	DIN 51130 EN 13893	R9 ≥ 0.3	R9 ≥ 0.3	R9 ≥ 0.3	R9 ≥ 0.3
<b>Thermal resistance</b>	DIN 52612	0.01 m <sup>2</sup> K/W	0.01 m <sup>2</sup> K/W		
<b>Underfloor heating</b>		Suitable - max. 27 °C	Suitable - max. 27 °C	Suitable - max. 27 °C	
<b>Colours</b>	—	24	30	12	18
<b>Form of delivery</b>	ISO 24341 (EN 426)	Rolls: 23 lm x 2 m	Rolls: 23 lm x 2 m	Rolls: 25 r m x 2 m	Rolls: 20 lm x 2 m
	ISO 24342 (EN 427)	Tiles: 61 x 61 cm on demand	Tiles: 50 x 50 cm 30 x 30 cm		Tiles: 61 x 61 cm 30 x 30 cm

The above information is subject to modifications for the benefit of further improvement (01/2013).  
For more detailed technical information, please contact Tarkett.