

## Technical Datasheet

Application: Plastic and rubber vapour control layers EN 13984: 2013

Style name **2009B** Language **English**  
 Type of carrier **Tyvek® HDPE with polymeric coating** Applicable for **UK, Ireland**

PROPERTY	METHOD	UNITS	NOMINAL	MINIMUM	MAXIMUM
Product designation acc. to EN 13984	-	-	B	-	-
<b>FUNCTIONALITY: WATER VAPOR AND AIR TIGHTNESS</b>					
Water vapour transmission range (sd)		m	0,2 ...35	-	-
Water vapour transmission (sd)	EN 1931	m	13	8	18
Density of water vapour flow rate (g)	EN 1931	kg / (m <sup>2</sup> s)	3,16E-08	5,14E-08	2,28E-08
Temperature resistance	-	°C	-	-40	+80
Water tightness	EN 13859-1 based on EN 1928 (A)	class	W1		
Durability (exposure to artificial ageing)					
Water vapour transmission properties	EN 1931	pass / no pass	(+)		
Gurley airpermeability	ISO 5636/5	s	2000	-	-
<b>PHYSICAL AND MECHANICAL PROPERTIES</b>					
Mass per unit area	EN 1849-2	g/m <sup>2</sup>	92	86	98
Thickness	EN 1849-2	µm	200	-	-
Reaction to fire	EN ISO 11925-2	class	E	-	-
Maximum tensile force (MD)	EN 12311-2	N/50mm	390	330	-
Elongation at max. tensile force (MD)	EN 12311-2	%	16	12	-
Maximum tensile force (XD)	EN 12311-2	N/50mm	380	330	-
Elongation at max. tensile force (XD)	EN 12311-2	%	19	14	-
Resistance to tearing MD (nail shank)	EN 12310-1	N	75	45	-
Resistance to tearing XD (nail shank)	EN 12310-1	N	65	40	-
<b>ADDITIONAL PROPERTIES</b>					
Length (customer related, expressed in m)	EN 1848-2	deviation in %	0	0	-
Width (customer related, expressed in mm)	EN 1848-2	deviation in %	0	-0,5	+1,5
Straightness	EN 1848-2	mm/10m	-	-	75
Resistance to impact	EN 12691	mm	(+)	-	-
Joint strength	EN 12317-2	N/5cm	-	280	-
Water column	EN 20811	m	3	-	-
Durability (against alkali)					
Elongation at max. tensile force (MD)	EN 12311-2	pass / no pass	pass	-	-
Elongation at max. tensile force (XD)	EN 12311-2	pass / no pass	pass	-	-

(+): No Performance Determined

**Effective date: 08/07/2020**

**First CE: 12/10/2017**

DuPont de Nemours (Luxembourg) S.à r.l.  
 Rue General Patton, L-2984 Luxembourg  
 DuPont (UK) Limited  
 Unit 29, Hither Green Estate, Clevedon  
 North Somerset, BS21 6XU

Tel +44 (0) 1275 337660  
 Fax +44 (0) 1275 879 773  
 tyvek.construction@dupont.com  
[www.tyvek.co.uk](http://www.tyvek.co.uk)

Some test methods are modified according to the EN 13984:2013 and/or according to the DuPont ISO 9001:2015 certified quality system (for details please contact your regional DuPont representative). All values are based on roll average. This information corresponds to our current knowledge on the subject. It is offered in accordance with REGULATION (EU) No 305/2011 OF THE EUROPEAN PARLIAMENT AND OF THE COUNCIL of 9 March 2011 laying down harmonised conditions for the marketing of construction products and repealing Council Directive 89/106/EEC. It is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for any application other than the application as specified herein. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions, DuPont makes no warranties and assumes no liabilities in connection with any use of this information for applications other than the application as specified herein. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right. Product safety information is available on request. This data sheet is a printed document and is valid without signature.