



Never compromise on quality!



LEVELMASTER STANDARD SELF-LEVELLING COMPOUND

Water-Based Cementitious Internal Levelling Compound



LEVELMASTER RANGE

CLASS
CT-C16-F4

Description:

A one part, cementitious, chloride/protein-free, levelling compound. When mixed with water it provides a smooth, level base for most common internal floor types such as concrete and sand/cement screed. Conforms to EN 13813 CT-C16-F4.

Benefits:

- ◆ *Self-smoothing.*
- ◆ *Accepts foot traffic after 3-4 hours depending on temperature and humidity.*
- ◆ *Preblended, requiring only the addition of water.*
- ◆ *Single pack and easy to use.*
- ◆ *Can be applied up to 6mm thickness.*

Uses

LevelMaster **STANDARD** is an ideal underlay for levelling most common internal subfloors prior to the installation of floor coverings. Note: Not suitable for use with under floor heating installations or areas subject to limited movement / vibration, unless used in conjunction with LevelMaster LATEX LIQUID. Alternatively, LevelMaster AD-FLOOR or LevelMaster AD-FLOOR PLUS should be used. **This product is not designed as a final wearing course to receive traffic and must be covered with either tiles, lino, vinyl, carpet, etc.**



Preparation

Surfaces must be clean, dry, structurally sound and free from grease, oil, paint, polish or any other contaminate that may hinder adhesion. **Porous surfaces** should be dampened down (without pooling or standing water). **Very absorbent surfaces** should be primed with a waterproof primer such as Bond It PRIMER & FLEXIBLE ADMIX or SBR. **Wooden floors** should be overboarded with 15mm exterior grade plywood rigidly fixed with screws at 300mm centres. The plywood should be primed as for very porous surfaces. **Anhydrite/calcium sulphate screeds** should be sanded and vacuumed before priming with 2 coats of Bond It PRIMER AND FLEXIBLE ADMIXTURE and left to dry for 24 hours prior to application. Note: PVA is not suitable for priming surfaces prior to application of LevelMaster **STANDARD**.



Mixing

Use 3.6L of clean water for every 20Kg bag of LevelMaster **STANDARD**. Slowly add the powder to the water while stirring

with a suitable slow speed drill or paddle. When using LATEX LIQUID refer to dosage on bottle.

Application

Pour the mix onto the subfloor within 10 minutes of mixing to a maximum thickness of 6mm. Use a flooring trowel or float to promote a smooth surface. This product can be built up to 10 - 12mm in thin layers, ensuring that the previous layer has fully hardened / cured. Allow adequate ventilation during curing. LevelMaster **STANDARD** will accept light foot traffic after 4 hours; however, floor coverings should not be laid for 24 hours (longer when used in conjunction with LATEX LIQUID).

Cleaning

All tools and equipment should be cleaned in water. Cured material can only be removed by mechanical means.

Limitations

Do not use at temperatures below 5°C or above 30°C. High temperatures will reduce the open time. Cold or humid conditions will slow the drying times. LevelMaster **STANDARD** does not provide a final wearing surface and must be covered with a floorcovering (ceramic tiles, wood flooring or carpet). Not suitable for use in conjunction with underfloor heating systems. Do not mix more material than can be used in 10 minutes.

Coverage

Depends upon the condition of the subfloor surface, however, a 20Kg bag will cover approximately 3.6m² at a depth of 3mm.

Storage Conditions

This product must be stored in unopened manufacturers bags away from extremes of temperature and in dry conditions. This product must be used within 12 months of manufacture and before the use by date shown on this bag.

Disposal of Containers

Do not leave empty containers where residue could be harmful to children, animals or the environment. Remove any containers to a central disposal point in accordance with local regulations.

Health & Safety

Please refer to separate material safety data sheet for full handling, use and storage instructions. Keep out of reach of children. It is the users responsibility to determine suitability for use. If in doubt contact our Technical Department for advice.

Note: this information is for general guidance only, since site conditions and labour are beyond our control. It is recommended that users make their own tests to determine suitability.

Specification Summary

Flammability	Non-flammable
Appearance	Grey granular powder
Setting Time	Foot traffic in 4 hours
Wet Density	2g/ml
UFI	GN20-K02W-A000-WSEC

Product Details:

Colour:	Grey	Grey
Colour:	BDH100B	BDH102B
Size:	10 Kg	20 Kg
Barcode:	5060021361318	5060021363282

CE

1029

BOND IT

G16 River Bank Way, Lowfields Business Park, Elland, West Yorkshire. HX5 9DN

13

EN13813 CT-C16-F4

Cementitious screed material for use internally in buildings

Reaction to fire	Class A1
Release of corrosive substances	CT
Water Permeability	NPD
Water Vapour Permeability	NPD
Compressive Strength	C16
Flexural Strength	F4
Wear Resistance	NPD
Sound Insulation	NPD
Sound Absorption	NPD
Thermal Resistance	NPD
Chemical Resistance	NPD



Part of the Bond It LevelMaster Range

The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies raw materials are also being used. The recommendations do not absolve the user from the obligation of investigating the possibility of infringement of third parties rights and, if necessary clarifying the position. Recommendations for use do not constitute a warranty, either expressed or implied, of the fitness or suitability of the products for a particular purpose.



Certificate Number:
6152
ISO 9001; ISO 14001;
ISO 45001



BOND IT
Head Office: Unit G16 River Bank Way, Lowfields Business Park,
Elland, West Yorkshire HX5 9DN.
Telephone: +44 (0)1422 315300 Fax +44 (0)1422 315310
Email: salesuk@bonditgroup.com Website: www.bonditgroup.com



V6 18/03/20
Supersedes: V5 04/03/19